

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
20 October 2005 (20.10.2005)

PCT

(10) International Publication Number
WO 2005/098059 A1

(51) International Patent Classification⁷: **C22B 15/06**,
5/10, 5/12

(21) International Application Number:
PCT/AU2005/000496

(22) International Filing Date: 6 April 2005 (06.04.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2004901900 7 April 2004 (07.04.2004) AU

(71) Applicant (for all designated States except US): **AUS-MELT LIMITED** [AU/AU]; 12 Kitchen Road, Dandenong, Victoria 3175 (AU).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **HUGHES, Stephen, Peter** [AU/AU]; 3 Iluka Street, Black Rock, Victoria 3193 (AU). **MATUSEWICZ, Robert** [AU/AU]; 27 Abbeygate Street, Oakleigh, Victoria 3175 (AU). **MCCLELLAND, Ross, Alexander** [AU/AU]; 1 Howell Drive, Berwick,

Victoria 3806 (AU). **ACQUADRO, Antony** [AU/AU]; 172 Dorking Road, Box Hill North, Victoria 3129 (AU). **BALDOCK, Brian, Ross** [AU/AU]; 49 McCormicks Road, Skye, Victoria 3977 (AU).


(74) Agent: **PHILLIPS ORMONDE & FITZPATRICK**; 367 Collins Street, Melbourne, Victoria 3000 (AU).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO,

[Continued on next page]

(54) Title: PROCESS FOR COPPER CONVERTING



(57) Abstract: The process for converting a copper sulphide matte to blister copper, is achieved by adding the copper sulphide matte and flux to a suitable agitated slag phase; and injecting, from a discharge tip at the lower end of a top-submerged lance, an oxidizing gas suitable for reacting with the matte to produce blister copper which forms or adds to a continuous blister copper phase below the slag phase. The lance tip is located within the slag phase at a depth enabling the injected gas to agitate the slag phase, and to react with copper sulphide matte dispersed therein, while precluding a substantial proportion of the gas from contacting the continuous blister copper phase.

WO 2005/098059 A1



SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

— *with international search report*